



NOTES: nts

- ① "SUBSTRATE": * TYPICAL NORMAL WEIGHT CONCRETE
- ② MVS: MOISTURE VAPOR SUPPRESSION, 2-COATS (1ST COAT 10 WET MILS, 2ND COAT 15 WET MILS)
- ③ WP: DECK SYSTEM WATERPROOFING COAT, APPLIED 40 WET MILS MINIMUM
- ④ BUILD: DECK SYSTEM BUILD COAT, 200 WET MILS MINIMUM IN 2 COATS (1ST COAT 100 WET MILS, 2ND COAT 100 WET MILS)
- ⑤ CLEAR: DECK SYSTEM CLEAR TOP COAT, 1 COAT APPLIED AT 20 WET MILS

* NORMAL WEIGHT CONCRETE IS PREFERRED. THE USE OF LIGHTWEIGHT STRUCTURAL CONCRETE REQUIRES USE OF MVS A/B (A38003 + A38101)

LAURENCO WATERPROOFING™ ©
A DIVISION OF FBC CHEMICAL CORPORATION

DECK - 001 TYPICAL DECK, HORIZONTAL OVER OCCUPIED SPACE